

PPSU

PPSU (Polyphenylsulfone) shows even better results in impact resistance and chemical resistance than PEI. It can operate in temperatures up to 180°C. This filament is based on a PPSU grade from Solvay. PPSU is an excellent choice for under-hood automotive applications and medical devices requiring repeated steam sterilization. The hydrolysis resistance is excellent compared to other amorphous thermoplastics. Besides that, it also resists common acids and bases over a broad range of temperatures.

Material features:

- High strength and toughness
- Excellent chemical and thermal resistance
- Good hydrolysis resistance
- Flame retardant
- Heat resistance up to 220°C

Colours:

PPSU is available in the colour natural.

NA1

Packaging:

PPSU is available on polycarbonate and carton spools.

Ask our team to help you customizing your product.

Filament specs.

Size	Ø tolerance	Roundness
1,75mm	± 0,05mm	≥ 95%
2,85mm	± 0,10mm	≥ 95%

Material properties

Description	Testmethod	Typical value
Specific gravity	ASTM D792	1,29 g/cm ³
MFI 365°C/5kg	ASTM D1238	14-20g/10min
Tensile strength at yield	ISO 527	77 MPa
Tensile strength at break	ISO 527	77 MPa
Elongation strain at break	ISO 527	60-120%
Elongation strain at yield	ISO 527	7,3%
Tensile (E) modulus	ISO 527	2410 MPa
Flexural strength	ISO 178	108 MPa
Flexural modulus	ISO 178	2380 MPa
Flame retardancy	UL94	V-0
Impact strength, Izod method 23°C notched	ISO 180	56,2 kJ/m ²
Printing temp.	Internal Method	370±20°C

Additional info:

Recommended temperature for heated bed is >140°C. Adhesion is possible on different surfaces.

PPSU can be used on desktop FDM or FFF technology 3D printers able to reach the high required temperatures. Dry the spool before printing: +4 hours at max. 110°C.

Storage: Cool and dry (15-25°C) and away from UV light. This enhances the shelf life significantly.

"The values presented in this publication are based on MCPP's knowledge and experience and are intended for reference purposes only. While MCPP has made every reasonable effort to ensure the accuracy of the information in this publication, MCPP does not guarantee that it is error-free, nor does MCPP make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. MCPP reserves the right to make any adjustments to the information contained herein at any time without notice. MCPP expressly disclaims warranties of any kind regarding the information contained herein, including, but not limited to, any warranties of merchantability or fitness of a particular purpose, use or application. MCPP shall not be liable for any damage, injury or loss induced from the use of MCPP's products in any application. Each user should thoroughly review this publication before selecting a product and, in view of the many factors that may affect processing and application of the product, each user should carry out their own investigations and tests and determining the safety, lawfulness, technical suitability, proprietary rights, and disposal/ recycling practices of the materials for the intended application."

